



Temperature correction factor for bursting pressure	-20°C	0°C	+23°C	+30°C	+40°C	+50°C	+60°C
	1,87	1,4	1	0,9	0,8	0,7	0,6

Hardness: 65 ShD.
Working temperature: From -30°C to +100°C.
Material: Poliyamide: PA6

ØD1	Working Pressure (bar)	Working pressure (psi)	Burst pressure (bar)	Burst pressure (psi)	Bending radius (mm)	LENGTH (M)
2,5x4 mm	36	522	108	1.566	20	25
4x6 mm	27	391,5	81	1.174,5	30	25
6x8 mm	20	290	60	870	40	25
8x10 mm	15	217,5	45	652,5	60	25
10x12 mm	13	188,5	39	565,5	85	25
2,5x4 mm	36	522	108	1.566	20	100
4x6 mm	27	391,5	81	1.174,5	30	100
6x8 mm	20	290	60	870	40	100
8x10 mm	15	217,5	45	652,5	60	100
10x12 mm	13	188,5	39	565,5	85	100