



Temperature correction factor for bursting pressure	-20°C	0°C	+23°C	+30°C	+40°C	+50°C	+60°C
	1,87	1,4	1	0,9	0,8	0,7	0,6

Hardness: 65 ShD.
Working temperature: From -30°C to +110°C.
Material: Poliyamide: PA12

ØD1	Ø in	Working Pressure (bar)	
4x6 mm	50	24	30
6x8 mm	70	15	30
8x10 mm	85	12	30
10x12 mm	110	12	30