

Properties	Method	Unit	Typical
Appearance	APM 27	-	clear
Density at 15°C	ASTM D 4052	kg/m³	886
Viscosity at 40°C	ASTM D 445	mm²/s	68.0
Viscosity Index	ASTM D 2270	-	108
Flash point COC	ASTM D 92	°C	222
Pour point	ASTM D 5950	°C	-24
Demulsibility at 54°C	ASTM D 1401	mins	25
Rust test/B	ASTM D 665	-	pass